

ITEM 220

LIME STABILIZED SUBGRADE

220.1 Description. This item shall consist of treating the subgrade, by the pulverizing, addition of lime, mixing and compacting the mixed material to the required depth and density, and in the amounts shown on the plans.

This item applies to natural ground, embankment, base or sub-base and shall be constructed to the sections, lines and grades shown on the plans. The subgrade shall be stabilized with lime for at least 6-inches depth, in the amount recommended by project plans and bid documents, and verified by Quality Assurance laboratory. The P.I. shall be determined by ASTM D4318.

220.2 Materials. Lime for stabilization shall be classified as:

Hydrated Lime; conforming to the requirements of the Item 221, "Hydrated Lime and Lime Slurry".

Commercial Lime Slurry; conforming to the requirements of the Item 221, "Hydrated Lime and Lime Slurry".

220.3 Equipment. The machinery, tools and equipment necessary for proper prosecution of the work shall be on the project and approved by the Engineer prior to the beginning of construction operations.

All machinery, tools and equipment used shall be maintained in a satisfactory and workmanlike manner.

Hydrated lime shall be stored and handled in closed weatherproof containers until immediately before distribution on the road. If storage bins are used, they shall be completely enclosed. Hydrated lime in bags shall be stored in weather proof buildings with adequate protection from ground dampness.

If lime is furnished in trucks, each truck shall have a weigh ticket from a certified scale. If lime is furnished in bags, each bag shall bear the manufacturer's certified weight. Bags varying more than 5 percent from that weight may be rejected and the average weight of bags in any shipment, as shown by weighing 50 bags at random, shall not be less than the manufacturer's certified weight.

220.4 Construction Methods. It is the primary requirement of this specification to secure a completed course of treated material containing a uniform lime soil mixture free from loose or segregated areas, of uniform density and moisture content, well bound for its full depth and with a smooth surface suitable for placing subsequent courses. It shall be the responsibility of the Contractor to regulate the sequence of his work, to use the proper

amount of lime, maintain the work and rework the courses as necessary to meet the above requirements.

The roadbed shall be constructed and shaped to conform to the typical sections, lines and grades as shown on the plans or as established by the Engineer. The subgrade shall be firm and able to support, without displacement, the construction equipment at the density herein specified. Any wet or unstable materials below the secondary subgrade shall be corrected, as directed by the Engineer, by scarifying, adding lime, and compacting, or other methods until satisfactory stability is obtained. The cost of the repair of the secondary subgrade and any materials below the secondary subgrade is incidental to this item.

The Contractor shall be required to roll the subgrade, as directed by the Engineer, before using the pulverizing machine and correct any soft areas that this rolling may reveal. This method will be permitted only where a machine is provided which will insure that the material is cut uniformly to the proper depth and which has cutters that will plane the secondary grade to a smooth surface over the entire width of the cut. The machine shall be of such design that a visible indication is given at all times that the machine is cutting to the proper depth.

220.5 Pulverization. Pulverize or scarify existing material after shaping so that 100% passes a 2 ½ inch sieve, prior to adding Lime. If material cannot be uniformly processed/pulverized to the required depth in a single pass, excavate and windrow the material to expose the secondary grade at typical sections, lines and grades as shown on the plans, or as established by the Engineer.

220.6 Application and Mixing the Lime. Lime shall be spread only on that area where the first mixing operations can be completed during the same working day.

The application and mixing of lime with the material shall be accomplished by the methods hereinafter described as "Dry Placing" or "Slurry Placing". When Hydrated Lime, is specified, the Contractor may use either method, unless otherwise noted on the plans.

When dry placing and before applying lime, bring the roadway (pulverized material) to its approximate optimum moisture content as determined by ASTM D698. Then the lime shall be spread by an approved spreader or by bag distribution at the rates shown on the Bid Sheet, or as directed by the Engineer.

The lime shall be distributed at a uniform rate and in such a manner as to reduce the scattering of lime by wind to a minimum. Lime shall not be applied when wind conditions, in the opinion of the Engineer, are such that blowing lime becomes objectionable to traffic or adjacent property owners. A motor grader shall not be used to spread the lime.

The material shall be sprinkled as directed by the Engineer, until the proper moisture content has been secured.

Where hydrated lime is specified and slurry placement is used, the hydrate shall be mixed with water to form a slurry of the solids content, as designated by the Engineer. A minimum of two mixing passes will be required.

Where commercial lime slurry is to be used, it shall be of the minimum solids and purity for the applicable grade being used. The distribution of lime shall be at the rates shown on the proposal form, or as directed by the Engineer. Proper application shall be attained by successive passes over a measured section of the roadway, until the proper moisture and lime content has been secured. The distributor truck shall be equipped with an agitator which will keep the lime and water in a uniform mixture.

Begin mixing within 6 hours of application of the lime. Hydrated lime exposed to open air for 6 hours or more between application and mixing, or has had excessive loss due to washing or blowing, will not be accepted for payment! The road material and lime shall be brought to the proper moisture content, thoroughly mixed by approved road mixers and the mixing continued until in the opinion of the Engineer, a homogenous, friable mixture of material and lime is obtained, free from all clods or lumps. Materials containing plastic clays or other materials which will not readily mix with lime, shall be pulverized in two or more stages, allowing for an intervening 24 to 48 hours mellowing period between each stage, then shall be mixed as thoroughly as possible at the time of lime application, then brought to the proper moisture content and allowed to mellow (cure) 48 to 96 hours, as directed by the Engineer. Sprinkle the treated materials during the mixing and mellowing operation, as directed, to achieve adequate hydration and proper moisture content, after mellowing is complete.

The material and lime shall be thoroughly mixed by approved road mixers or other approved equipment, and the mixing continued until, in the opinion of the Engineer, a homogenous friable mixture of material and lime is obtained, such that when all non-slaking aggregates retained on the 3/4-inch sieve are removed, the remainder of the material shall meet the following requirements when tested in accordance with ASTM Method C136, from samples procured from the roadway, and meet the gradation requirements in Table I.

TABLE I

Minimum Passing 1 3/4" sieve	100 Percent
Minimum Passing 3/4" sieve	85 Percent

If gradation is achieved on the first mixing, no additional mixing is required.

- 220.7 Compaction. Compaction of the mixture shall begin immediately after final mixing unless approval has been obtained from the Engineer not to do so. The material shall be aerated and/or sprinkled as necessary, to provide the optimum moisture content. Compaction shall begin at the bottom and shall continue until the entire depth of mixture is uniformly compacted. The subgrade shall be compacted to a minimum of 95-percent of standard proctor density (ASTM D698) at a moisture content of optimum to 3-percent above optimum.

In addition to the requirements specified for density, the full depth of the material shown on the plans shall be compacted to the extent necessary to remain firm and stable under construction equipment. After each section is completed, tests as necessary will be made by the Engineer. If the material fails to meet the density requirements, it shall be reworked as necessary to meet these requirements. Throughout this entire operation, the shape of the course shall be maintained by blading and the surface upon completion shall be smooth and in conformity with the typical section shown on the plans and to the established lines and grades. Should the material, due to any reason or cause, lose the required stability, density and finish before the next course is placed or the work is accepted, it shall be reprocessed and refinished at the expense of the Contractor.

- 220.8 Finishing. After the final course of the lime treated subgrade has been compacted, it shall be sprinkled and rolled, as directed by the Engineer. All irregularities, depressions or weak spots which develop shall be corrected immediately by scarifying the affected areas, adding or removing material as required, and reshaping and re-compacting by sprinkling and rolling. It shall be brought to the required lines and grades in accordance with the typical sections. The completed section shall then be finished by rolling as directed with a pneumatic tire or other suitable roller sufficiently light to prevent hairline cracking. The completed section shall be prime coated and asphalt emulsion cured for a minimum of 24 hours, and then covered by base material. If the plans provide for the treated material to be sealed or covered by other courses of material, such seal or course shall be applied within 14 days after final mixing and compaction is completed, unless otherwise directed by the Engineer.

- 220.9 Quality Assurance. The Testing Laboratory's representative will determine the Moisture-Density Relationships in accordance with ASTM D698 on material secured from the roadway after stabilization with lime, for each type of material encountered.

The Testing Laboratory's representative will determine the in-place density in accordance with ASTM D6938 or D1556. The minimum level of testing will consist of at least three tests for each 500 feet per lift per lane of roadway or 4,000 square feet of embankment.

220.10 Measurement. Manipulation of lime during the stabilization of the subgrade shall be measured by the square yard of subgrade actually stabilized.

Lime shall be measured as follows:

- A. Hydrated lime shall be measured by the ton of 2,000 pounds, dry weight.
- B. Commercial lime slurry shall be measured by the ton of 2,000 pounds of lime "dry solids", in the slurry. The quantity of lime shall be calculated from the minimum percentage of solids as described in Item 221, such as the following example:

Grade 2: At least 35 percent by weight of slurry and calculate the quantity of lime by the ton of 2,000 pounds, based on 35 percent lime content.

220.11 Payment. Payment for manipulation of "Lime Stabilized Subgrade" shall be made at the contract unit price per square yard of compacted subgrade for the depth specified.

The unit price bid shall be full compensation for loosening, mixing, pulverizing, spreading, drying, application of lime, water content of the slurry, compaction, shaping and maintaining for all manipulations required, for all hauling and freight involved, for all tools, equipment, labor and all incidentals necessary to complete the work.

Payment for "Lime" shall be made at the contract unit price per ton of lime used for stabilizing the subgrade. See Item 221.

There are line code(s), description(s), and unit(s) for this item.

END OF ITEM 220